



LABORATORY GROWN DIAMOND IDENTIFICATION REPORT

LG450025915
 ANTWERP, November 11, 2020

**LABORATORY GROWN
DIAMOND**
OVAL BRILLIANT
WEIGHT 0.70 CARAT
COLOR D
CLARITY SI 1
POL-SYM EXCELLENT
PROP EXCELLENT
FLUO NONE

6.88 x 5.13 x 3.15 mm


Pointed

Note: Profile not to actual proportions

NUMBER LG450025915ANTWERP, November 11, 2020

DESCRIPTION LABORATORY GROWN DIAMOND

SHAPE AND CUT OVAL BRILLIANT

CARAT WEIGHT 0.70 CARAT

Measurements 6.88 x 5.13 x 3.15 mm

CLARITY GRADE SI 1

COLOR GRADE D

Fluorescence NONE

FINISH
Polish - Symmetry EXCELLENT

Proportions EXCELLENT

Table Size 57%

Crown Height 15%

Pavilion Depth 42%

Girdle Thickness MEDIUM TO SLIGHTLY THICK (FACETED)

Culet POINTED

Total Depth 61.4%

COMMENT This Laboratory grown diamond was created by high pressure high temperature process (HPHT). Type II

LASERSCRIBE LABGROWN IGI LG450025915

Hearts & Arrows
CLARITY SCALE

FLAWLESS/ INTERNALLY FLAWLESS	VERY VERY SLIGHTLY INCLUDED		VERY SLIGHTLY INCLUDED		SLIGHTLY INCLUDED		INCLUDED		
	VVS ₁	VVS ₂	VS ₁	VS ₂	SI ₁	SI ₂	I ₁	I ₂	I ₃

COLOR SCALE

COLORLESS			NEAR COLORLESS			SLIGHTLY TINTED			VERY LIGHT			LIGHT			FANCY COLOR							
D	E	F	G	H	I	J	K	L	M	N	O	P	Q	R		S	T	U	V	W	X	Y

The laboratory grown diamond described in this report has been graded, tested, analyzed, examined and/or inscribed by International Gemological Institute (IGI). Laboratory grown diamonds are diamond crystals created by scientific means and representing essentially all physical, chemical and optical characteristics of natural diamonds. IGI employs and utilizes those techniques and equipment currently available to IGI including without limitations: DiamondView, DiamondSure, FTIR spectroscopy, UV VIS NIR absorption spectrometer, EDXRF spectroscopy, PL (RAMAN) spectrometers.

Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.


 See terms
and conditions on reverse

© IGI 2000 edition 2015

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute

